

# ULTRA-THANE 205 HFO HL WALL

## SPRAY POLYURETHANE FOAM - INTERIOR USE

ULTRA-THANE 205 HFO HIGH-LIFT WALL is a two-component interior, spray-in-place closed cell, medium density polyurethane foam insulation providing superior performance in minimizing heat transfer, condensation and air leakage.

Ultra-Thane 205 HFO HL Wall is based on Low GWP Hydrofluro-olefin (HFO) Technology to expand the polyurethane polymer into a cellular insulation.

### RECOMMENDED USES

Ultra-Thane 205 HFO HL Wall Foam is the insulation of choice for maintaining the climate controlled cold storage interior insulation conditions and for mitigating condensation in cold storage and freezer buildings. For interior use only.

TANK INSULATION: Ultra-Thane 205 HFO HL Wall Foam is an excellent rigid thermal insulation for constant temperature requirements.

### PACKAGING

Ultra-Thane 205 HFO HL Wall Foam is sold in 975 lbs., two-component drum kits. Side-A totes are available upon request.

### MAXIMUM PASS THICKNESS

4.0 inches



### PHYSICAL PROPERTIES

Property	ASTM Standard	Results
Sprayed-In-Place Density	D1622	2.2 ± 0.1
Dimensional Stability @ 158°F 97% RH (168 h)	D2126	<7%
R-Value aged (1.0-inch thickness)	C518	7.9
R-Value aged (3.0-inch thickness)	C518	23
Compressive Strength	C1621	35 psi
Tensile Strength	D1623	50 psi
Water Vapor Permeance (Procedure A)	E96	0.73@ 1", 0.53@ 2"
Air Permeance @ 1"	E2178 @75 PA	<0.031 L/sm <sup>2</sup>
Shear Strength	C273	45
Closed Cell Content	D6226	93%
Water Absorption	D2842	1.07%

This information is intended only as a guide for design purposes. The values shown are the average values obtained from laboratory prepared samples and results may vary with application conditions, equipment and technician.

Typical density for wall foam is 2.2 pcf. For higher density, exterior foams, see ULTRA-THANE 230 ROOF FOAM data sheet.

## BUILDING AND FIRE CODES

FIRE TEST RESULTS		
Flammability : Class A (Class 1)	ASTM E84 @ 4"	<25 Flame Spread   <200 Smoke Development
Large Scale Fire Testing: Ignition Barrier	AC 377 Appendix X*	PASS: NO COATING
Large Scale Fire Testing: Thermal Barrier	NFPA 286*	PASS: 16 Wet Mils DC 315
UPC 2.0 HFO meets or exceeds the IBC requirements for exterior walls in type I, II, III, IV and V construction. This includes NFPA 285 and NFPA 259 testing with Intertek Listings (GWL/FIP 30-02, GWL/FIP 30-03).		

- Meets the code compliance ICC-1100 and ICC-AC377.
- Intertek in CCRR 0375 evaluated and listed.
- Meets building codes: IBC, IRC and IECC
- Interior use only and must be protected by a 15-minute rated thermal barrier or as permitted by building codes.

## PROCESSING GUIDE

PROPERTY	SPRAYED*		
Reactivity Grades	Winter	Regular	Summer
Cream Time	1-2 Seconds	1-2 Seconds	1-3 Seconds
Rise Time	4-5 Seconds	5-6 Seconds	5-7 Seconds
Tack Free	On Rise	On Rise	On Rise
*Specific reaction times and densities are available by request.			

LIQUID COMPONENT PROPERTIES	
Property	Results
Color Component A Component B	Dark Brown Amber/Brown
Viscosity @ 77°F (25°C) Component A Component B	200 650
Specific Gravity @ 77°F (25°C) Component A Component B	1.24 1.21
Mix Ratio A/B	50/50
Nominal 1" thickness sprayed through Graco Reactor E-30 proportioner with Fusion AP Gun, AR 4242 mixing chamber: preheat set at 120°F, hose heat set to maintain 120°F at the spray gun. Reaction times are influenced by mix efficiency of the spray gun, temperature of the components, ambient conditions and thickness of the foamed mass.	

## REQUIREMENTS

Ultra-Thane 205 HFO HL Wall is a sophisticated plural component building product which should be applied only by trained and manufacturer-approved insulation experts familiar with the properties of this material.

## SUBSTRATE TEMPERATURE

Ultra-Thane 205 HFO HL Wall may be applied to surfaces with temperatures as low as 20°F (-7°C) in most instances.

REACTIVITY GRADES AND TEMPERATURE RANGES		
Winter	Regular	Summer
20 to 60°F	60 to above 90°F	90 to above 120°F
-7 to 16°C	16 to above 32°C	30 to above 49°C

## SUBSTRATE PREPARATION

For optimum results, the interior surfaces should be clean and dry, free of dirt, oil, solvent, grease, loose particles, peeling coating and other foreign matter. For tanks, untreated ferro-metallic substrates should be sandblasted in accordance with SSPC-SP6. Sandblasted surfaces should be primed immediately with an approved primer.

Galvanized and stainless-steel surfaces should be treated and primed with Ultra-Bond 40 metal primer prior to use of Ultra-Thane 205 HFO HL Wall .

Porous substrates such as wood and concrete may not require priming if surfaces are clean and dry with less than 10% moisture content. **FOR BEST RESULTS ON SURFACES WHERE MOISTURE CONTENT CANNOT BE DETERMINED OR CONTROLLED, AN EPOXY SEALING PRIMER IS RECOMMENDED.** Consult General Coatings Manufacturing Corp. for specific application requirements.

## EQUIPMENT

Proportioning equipment shall be manufactured specifically for the application of polyurethane foam. Mixing ratio by volume is 50 parts "A" to 50 parts "B". Equipment shall be of the heated airless type, capable of maintaining 120°F to 140°F (49 to 60°C) mixed material at the spray gun. Optimum spraying temperature will vary as a function of substrate and ambient conditions.

## SPRAYING

Ultra-Thane 205 HFO HL Wall should be installed in uniform layers ranging from 1/2" to 3" maximum pass thickness. Foam application thicknesses will vary as a function of substrate temperature, humidity, and applicator technique. Ultra-Thane 205 HFO HL Wall bonds best when previous pass is still warm (above 70°F). Ultra-Thane 205 HFO HL Wall must be coated with thermal barrier or ignition barrier during the same day of application. For exterior tanks, it may be left exposed for up to 24 hours before coating system installation.

**CLIMATIC CONDITIONS:** No spraying should be done when moisture is present in the form of rain, dew or relative humidity greater than 80%, or when there is wind in excess of 15 mph for exterior tank application.

## SPECIAL NOTE

Particular attention must be paid to exterior coating selection in tank applications where a vapor drive exists. Consult General Coatings Manufacturing Corp. technical service personnel for specific system recommendations.

## LIMITATIONS

Ultra-Thane 205 HFO HL Wall is specifically designed for construction applications where the end use ambient temperature range will be maintained between -100°F to 200°F (-73 to 93°C). When considering any other use for this product, consult General Coatings Manufacturing Corp. for specific application recommendations.

## THERMAL BARRIER

Application without a Prescriptive Thermal Barrier: The insulations may be installed without the 15-minute thermal barrier prescribed in IBC Section 2603.4 and IRC Section R316.4, when installed as described in this section. The insulation must be covered with one of the following coatings:

- DC315: Maximum thickness of foam plastic of 8 inches on walls and 12 inches on ceilings, covered on all surfaces with DC315 applied at 16 wet mils (1.12 gal/100 ft<sup>2</sup>).
- No Burn Plus ThB: Maximum thickness of foam plastic of 6-1/2 inches on walls and 9-1/2 inches on ceilings, covered on all surfaces with No Burn Plus ThB applied at 14 wet mils (0.90 gal/100 ft<sup>2</sup>).

## VAPOR RETARDER

Ultra-Thane 205 HFO HL Wall is intended for indoor applications, and is a class II vapor retarder at 1 inch.

## JOB-SITE PROTECTION

Applicators should ensure the safety of the job-site and construction personnel by posting appropriate signs warning that all "hot work" such as welding, soldering, and cutting with torches should not take place until a thermal barrier or approved equivalent is installed over any exposed polyurethane foam.

Contractors should communicate with other trades working in proximity to the spray application area. Appropriate warning signs at each entryway must be posted that clearly indicates that spray foam activity is taking place and proper respiratory protection is required to enter. Non SPF personnel and occupants should be vacated from the building during the application of SPF. Proper Ventilation during is required during spraying and afterwards, at minimum 10 Air changes per hour.

Re-Entry: 2 hour ventilation period before personal protective equipment is no longer required for trades and inspectors.

Re-Occupancy: after 24 hours.

LARGE MASSES of SPF should be removed to an outside safe area, cut into smaller pieces and allowed to cool before discarding into any trash receptacle.

As with all SPF systems improper application techniques should be avoided. Examples of improper application techniques include, but are not limited to excessive thickness of SPF, off-ratio material and spraying into or under rising SPF. Potential results of improperly installed SPF include: dangerously high reaction temperatures that may result in fire and offensive odors that may or may not dissipate. Improperly installed SPF must be removed and replaced with properly installed materials.

## FREIGHT CLASSIFICATION

Liquid Plastic Material - NOIBN

## SHELF LIFE AND STORAGE

The shelf life of Ultra-Thane 205 HFO HL Wall is 6 months from the date of manufacture when stored in original unopened containers at temperatures between 50–75°F (10-24°C). Note: Storage for prolonged periods of time at high temperatures may alter the reactivity profile of the product. Additionally, storing the B component at increased temperatures or in direct sunlight for prolonged periods may cause a buildup of pressure in the storage vessel. Use caution in opening containers of Ultra-Thane 205 HFO HL Wall. Containers should be opened slowly to allow the release of any pressure buildup. Material temperature should be confirmed with a thermometer or an infrared gun.

## HEALTH & SAFETY

A Safety Data Sheet (SDS) has been prepared on the Ultra-Thane 205 HFO Wall. All personnel who will come in contact with the product should read and understand the SDS.

In addition to reading and understanding the SDS, all contractors and applicators must use appropriate respiratory, skin and eye Personal Protective Equipment (PPE) when handling and processing polyurethane chemical systems.

Spray Polyurethane Foam Alliance (SPFA®): PCP Certification Program: Health, Safety and Environmental Aspects of Spray Polyurethane Foam and Coverings. [www.Sprayfoam.org](http://www.Sprayfoam.org)

The Center for the Polyurethanes Industries (CPI): Model Respiratory Protection Program for Compliance with the Occupational Safety and Health Administration (OSHA) Standard 29 CFR§1910134. [www.spraypolyurethane.org](http://www.spraypolyurethane.org).

## PERSONAL PROTECTIVE EQUIPMENT

Ultra-Thane 205 HFO HL Wall requires personal protective equipment, such as, approved full face fresh air breathing system, gloves and coveralls. Spray Foam (A-Side) contains polymeric MDI isocyanate, which is a vapor inhalation and skin hazard. See Safety Data Sheet for best practices and health risks.

## VAPOR INHALATION

The best form of protection against organic solvents or potentially sensitizing vapors in the workplace is a fresh air supply. Numerous manufacturers, including the 3M Company and MSA, make full face fresh air masks. For maximum protection, we recommend use of NIOSH/MSHA approved self-contained breathing apparatus with a full-face piece operated in a positive pressure mode. In well-ventilated application conditions, the use of Type C organic vapor cartridge respirators is acceptable.

Effects of overexposure to vapor are characterized by nasal and respiratory irritation, dizziness, nausea, headache, fatigue, possible unconsciousness or even asphyxiation. Vapor inhalation problems are characterized by coughing, shortening of breath and tightness in the chest. Anyone exhibiting these types of symptoms should be immediately removed from the workplace and administered oxygen or fresh air. If the condition is prolonged or extreme, SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

## SKIN CONTACT

To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves. Skin contact with liquid components can result in a rash or other irritation. Wash the affected skin area with water. Wipe residual liquid from the skin with a clean cloth, then wipe the affected area with 30% solution of rubbing alcohol. Follow the alcohol wipe with repeated washings with soap and

water. If a rash or other irritation develops, see a physician.

## EYE CONTACT

Wear a full-face mask or OSHA-approved protective goggles. Eye Contact with liquid or sprayed components can result in corneal burns or abrasions. Upon exposure, eyes should be flushed with water for an extensive period. SUMMON EMERGENCY TRAINED MEDICAL ATTENTION IMMEDIATELY.

## TECHNICAL SERVICES

Additional information, such as brochures, technical assistance, roof energy evaluations, life cycle cost analysis, and other roof management services are also available from a General Coatings Manufacturing Corp. Technical Consultant.

**LIMITED WARRANTY.** Please read all information in the General Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. These products are for professional use only and to be applied by professionals who have prior experience and training with the use and application of our materials, and who are fully aware of all Federal, State and local rules, regulations, and code requirements for storage, transportation, handling, installation, and application. Published technical data and instructions are subject to change without notice. Contact your local representative or visit our website for current technical data, SDS, instructions, and project specific recommendations. We warrant our products to be free of manufacturing defects and that they will meet our current published physical properties within the shelf life of products.

Our sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. We will not be liable for damages of any sort, including remote or consequential or punitive damages resulting from any claimed breach of any warranty whether expressed or implied. We will also not be responsible for use of this product in a manner to infringe on any patent held by others. No warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, adhesion, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. We reserve the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Your sole and exclusive remedy against us shall be limited to the paid cost of the materials sufficient to replace any affected areas where product failure has occurred. The cost of replacement materials shall, in no event, exceed the value of the original purchase price of the products, subject to equitable reductions for time of use.

**DISCLAIMER:** We are not a professional contractor, engineering company, consultant, or applicator. We are a manufacturer and we are not a designer/engineer/applicator of record and do not provide advice. We do not specifically review, endorse, or approve of any proposals, owner's specifications, project specifications, or other arrangements. All guidelines, recommendations, statements, and technical data contained herein are based on information and tests conducted in controlled conditions and do not represent applicable for all environments and we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. As a user, you will remain responsibility to satisfy yourself, based on your own information and test, to determine suitability of the product for your own intended use, application and job situation and you assume all risk and liability resulting from use of the products. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. We are not liable to any user or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. No recommendations or statements, whether verbal or in writing, shall be binding upon us except as provided herein, or as provided in writing and signed by an authorized corporate officer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Not responsible for typographical errors.

© 2026 General Coatings Manufacturing Corporation. All Rights Reserved. Revision ULTRA-THANE 200 HFO HIGH-LIFT\_04262026.AG

1220 E. North Avenue | Fresno, CA 93725 | T: (559) 495-4004 | F: (559) 495-4009 | Toll Free: (855) 495-GCMC | [www.GeneralCoatings.net](http://www.GeneralCoatings.net)