

PENEFIL 250HR

PENEFIL™ Products PORTFOLIO

The PENEFIL portfolio features proprietary, two-component closed cell resin systems designed for geotechnical applications, encompassing precision slab lifting, soil compaction, soil stabilization, and void filling. Each production batch undergoes exhaustive quality-controlled analysis, mechanical property validation, and ISO-compliant quality assurance protocols to guarantee uncompromised field efficacy and long-term durability.

RECOMMENDED USES

Concrete Slab Lifting and Stabilizing | Foundations repairs and leveling | Erosion Restoration | Sidewalks | Patios | Pool Decks | Porches | Basement Slabs | Concrete Stoops | Foundations | Tanks

REACTIVITY PROFILE at 110 °F

Cream Time	2-5
Gel Time	5-15
Tack Free Time	15-20
Rise Time	20-25
Cure Time	>90% in 30 min, Full cure in 24 Hrs.

RECOMMENDED PROCESSING PARAMETERS

A-Side Temperature	85-140 °F
B-Side Temperature	105-140 °F
Hose Temperature	110-140 °F
Pressure	1000 psi
Ground Temperature	>50 °F
Mix Ratio	1:1

PENEFIL 250HR

PENEFIL™ 250HR is 2.5 lbs. hydrophobic/hydro-insensitive, water- blown, rigid, slab- jacking foam designed to raise and stabilize concrete slabs or asphalt roadway in residential uses. PENEFIL 250HR delivers a low-viscosity, dual-component resin system optimized for effective remediation of settlement issues in foundations, roadways, sidewalks, and slabs—particularly ideal for injection equipment with limited capacity for high-viscosity materials.

ADVANTAGES

- Contains NO Solventes, ZERO-ODP, ZERO-GWP
- Water Blown System
- Low Viscosity
- Compacts loose soil
- Fast expansion and reactivity

PHYSICAL PROPERTIES

Physical Properties	Test Method	Free Rise
Density	ASTM D1622	2.3 – 2.7 pcf
Compressive Strength	ASTM D1621	40 – 50 psi
Close Cell Content		>90%

COMPONENTS PROPERTIES

Properties	Isocyanate	PENEFIL 2.5H
Color	Brown	Clear
Viscosity (77 °F)	180-200 cps	600-900 cps
Shelf-life (unopened drums)	12 months	6-months
Storage Temperature	50-105 °F	50-105 °F

The viscosity of both components decreases with increasing temperature. The foam reactivity increases with increase in temperature.

REQUIREMENTS

PENEFIL 250HR is an injection concrete lift foam system intended for installation by qualified contractors trained in the processing and application of systems, as well as the plural-component polyurethane dispensing equipment required to do so.

Handling/Storage Conditions/Shelf-Life

The shelf life of PENEFIL 250HR Foam is 6 months from the date of manufacture when stored in original unopened containers at temperatures between 50-75 °F (10-24 °C). Note: Storage for prolonged periods of time at high temperatures may alter the reactivity profile of the product. Additionally, storing the B component at increased temperatures or direct sunlight for prolonged periods may cause a buildup of pressure in the storage vessel. Use caution in opening containers of PENEFIL 250HR. Containers should be opened slowly to allow the release of any pressure buildup. Material temperature should be confirmed with a thermometer or an infrared gun. Do not expose A-side component to low temperatures as it may freeze.

Application Guidelines

When applying PENEFIL 250HR, it is important to note the application of foam is dependent on temperature, humidity, elevation, substrate, equipment and other factors. The applicator must constantly observe the characteristics of the sprayed foam and adjust processing temperatures and pressures to obtain the correct cell structure, adhesion, cohesion and general quality of foam. When changing between

different resin systems, flush adequate amount of material through the gun to clear hose lines of previous material. Application of slab-jacking foam requires specialized gun adapter parts.

CAUTION

This product is not combustible. Not intended or fire classified for interior use. Wear proper protective equipment while handling this product.

LIMITED WARRANTY. We warrant our Products to be free of manufacturing defects and to comply with the Product's current published physical properties when tested under controlled conditions. Our sole responsibility is limited to replacement of that portion of any Products found to be defective at the time of manufacture. There are no other warranties of any nature whatsoever, whether expressed or implied, including an express disclaimer of any warranty of merchantability or fitness for a particular purpose. Further, we disclaim any liability for damages of any type, however caused, including remote, consequential damages, or special damages resulting from any theory of liability, whether based on tort, negligence, or strict liability. We disclaim responsibility for any claims of intellectual property infringement through use of our Products in any manner. Where Products are used as a waterproofing membrane or floor coating, no warranty or guarantee is issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, abnormal wear and tear, or improper application by the applicator. Damage caused by abuse, neglect, lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are aLPo excluded. In all instances and as a pre-condition to any available remedy, we reserve the right to conduct sample testing and performance analysis on any materialLP claimed to be defective, performed prior to any repairs being made by owner, general contractor, or applicator. Our limited warranty is void if repairs have been made or attempted, or if the claimed defect has been adulterated prior to our ability to conduct a formal investigative analysis.

DISCLAIMER: Please read all information in the general guidelines, technical data sheets, application guide and safety data sheets (SDS) before applying material. Products are for professional use only and should only be applied by professionalLP who have prior experience with our Products or have undergone specific training in their proper application. Published technical data and instructions are subject to change without notice. Contact your local representative or visit our website for current technical data and instructions. All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of these tests are not guaranteed and are not to be construed as a warranty, either expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with any product. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his own use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. We are not liable to the purchaser, end-user, or any third party for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, our Products. Recommendations or statements, whether verbal or in writing, shall not be binding upon us unless in writing and signed by one of our authorized corporate officers. Technical and application information is provided for establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and we make no claim that these tests or any other tests, accurately represent all environments. We are not responsible for typographical errors.
© General Coatings Manufacturing Corporation. All Rights Reserved.
Revision PENEFIL 250_08172020EA